

فرآورده های فرعی / بخش فولادسازی



مشخصات سرباره کنورتور

9-11%	SiO ₂
2-5%	MnO
0.7-1.4%	Al ₂ O ₃
50-57%	CaO
2-4%	MgO
2.0-3.0%	V ₂ O ₅
2.3-3.2%	P ₂ O ₅
10-15%	TFe
10-14%	FeO
2.0-3.0%	TiO ₂

مشخصات لجن صنعتی کنورتور

50 - 60%	TFe
7-15%	FeO
1.5-3.0%	SiO ₂
5-13%	CaO
0.5-1.0%	MgO
0.1-1.0%	Al ₂ O ₃
1.0-2.5%	MnO
0.1-0.2%	S

آهک میکرونی سیکلون

≈ 80%	CaO
-------	-----